



Technical data sheet

INVEBI Industrial coatings – Italy

1532/3AZ

FLOOR MATERIC COATING-NEUTRAL

Product: Water-based single-component product for inside covering.

Introduction: Quartz product designed for the construction of spatulated monolithic floor and wall coverings with the possibility of obtaining different effects such as clouded, sponged, textured, etc. Rasodecor has an excellent anchorage on almost all materials: ceramic, parquet, wood, etc. The support must be clean and dry, free of inconsistencies and loose parts. Apply with a smooth trowel or other equipment as desired, taking care not to overdo the thicknesses otherwise cracks may occur, which may sometimes even be desired, due to the withdrawal of the material during the drying phase. The product can be 5% pigmentable with our I550 series pastes.

Kind of use: Flooring, cladding, interior renovations

Support type: Ceramics, parquet, masonry walls, etc.

Characteristics :

Flash-point : Please revert to SDS	1. Viscosity	• Paste aspect
	2. Solid content A (Paint)	• 85% +/- 1%
	3. Practical useful life at 20°C 60% U.r.	• Unlimited
	4. Dust free at 20°C, 60% U.r	• 6 - 8 h
	5. Touch dry at 20°C 60% U.r	• 10 – 12 h
	6. Dry in deepness at 20°C 60% U.r	• 24 – 36 h

Application : By spatula/roller.

	Code - Information	Specific weight	mix by gr.	mix by ml.
Paint :	1532/3AZ - Rasodecor Sp RESINE	1,25	100	100

Quantity to be applied :

- Thicknesses of approximately 1–2 mm; the theoretical yield depends on the particle size of the product to be applied, the thickness and the type of processing to be carried out. Generally, about 3.5 kg of product per square meter are required to achieve an approximate thickness of 2 mm when using Rasodecor.

Sanding :

- After about 16 – 24 h

Over coating :

- After about 6 – 8 h, with wb or sb products.

Storage :

at 20°C 8 months (in the original sealed packing) part A

at 20°C months (in the original sealed packing) part B

please note that the water-based products must always be kept at a temperature higher than 5 ° C to avoid freezing.

General notes : always mix the products before use

Invebi does not assume any responsibility for the improper use of products.

All information and advices (oral, written or any other form) provided by Invebi, even if representing the highest level of our knowledge, can not be considered legally relevant. Our support does not exempt the customer from the duty of previously verifying all information and advices with particular reference to technical and safety data sheets.

IT IS A DUTY OF THE CUSTOMER TO MAKE SURE THAT THE USE OF OUR PRODUCTS IS SUITABLE BEFORE THE APPLICATION AND IN ACCORDANCE WITH ITS REQUIREMENTS, LAWS, REGULATIONS AND PATENTS IN FORCE.