



Technical data sheet

INVEBI Industrial coatings – Italy

2067/AZ

NITRO WHITE SEALER HIGH COVERING

Product: Nitro pigmented base coat

Introduction: It is a white nitrobased base coat with good resistance to overlapping, good also the cover, the sanding and the full. It is specifically formulated for products that must be exposed inside homes.

Kind of use: Furniture, manufactured products generally turned etc.

Support type: MDF or essences also for open pore cycles etc.

Characteristics : Flash-point : Please revert to SDS	1. Viscosity BROOKFIELD20°C	• 45000 CPS
	2. Viscosity Ford 4 20°C after catalysis	• /
	3. Solid content A (Paint)	• 77% +/-1%
	4. Solid content B (1°hardner)	• /
	5. Solid content A+B (paint+1°hardner)	• /
	6. Pot-life (Life in pot 100 gr/20°C)	• Unlimited
	7. Practical useful life at 20°C 60% U.r.	• Unlimited
	8. Dust free at 20°C, 60% U.r	• 15 – 20 min
	9. Touch dry at 20°C, 60% U.r	• 60 – 90 min
	10.Dry in deepness at 20°C 60% U.r	• 8 – 10 hours
	11. Forced drying 40-45°C	• 3 – 4 hours
	12. Light stability	• Yellowing

Application : Spray with cup or pressure spray guns

	Code - Information	Specific weight	mix by gr.	mix by ml.
Paint :	2067/AZ	1,62	100	100
Thinner :	105/AZ - NC thinner	0,82	30-50	60-100

Quantity to be applied :

Sanding :

Over coating :

Storage :

- 100 - 150 gr/sqm
 - After 10 hours at 20°C
 - With white or pigmented nitro top coats.
- at 20°C 8 months (in the original sealed packing) part A
- at 20°C months (in the original sealed packing) part B
- please note that the water-based products must always be kept at a temperature higher than 5 ° C to avoid freezing.
- General notes :** always mix the products before use

N°1 - 01/06/2023

Invebi does not assume any responsibility for the improper use of products.

All information and advices (oral, written or any other form) provided by Invebi srl, even if representing the highest level of our knowledge, can not be considered legally relevant. Our support does not exempt the customer from the duty of previously verifying all information and advices with particular reference to technical and safety data sheets.

IT IS A DUTY OF THE CUSTOMER TO MAKE SURE THAT THE USE OF OUR PRODUCTS IS SUITABLE BEFORE THE APPLICATION AND IN ACCORDANCE WITH ITS REQUIREMENTS, LAWS, REGULATIONS AND PATENTS IN FORCE.