



Technical data sheet

INVEBI Industrial coatings – Italy

2665/AZ WATER BASED MATT BINDER FOR TILES AVAILABLE IN DIFFERENT GLOSSES**

Product: Transparent water-based finishing primer for resin, ceramic, glass, and tiles.

Introduction: High-solids content polyurethane topcoat developed for application on a wide range of surfaces, including resin, ceramic, glass, and tiles. It provides excellent direct adhesion to glass and ceramic tiles. The product is characterized by outstanding mechanical and chemical resistance, excellent surface wetting, high surface hardness, superior abrasion resistance, and excellent UV stability.

It can be used as a single-component coating or catalyzed at 10% with IV220/AZ to further enhance adhesion and chemical resistance. Once catalyzed, the mixture has a pot life of up to 4 hours and should be applied within this period to ensure optimum performance.

This product is an ideal professional solution for creating modern, durable, and highly resistant surfaces.

Kind of use: Parquet, stairs, glass and tiles, indoor and outdoor furniture.

Support type: Resin floors, microcements, tiles etc.

Characteristics : Flash-point : Please revert to SDS	1. Viscosity Ford 4 20°C	• 47'' +/- 2''
	2. Viscosity Ford 4 20°C after catalysis	• /
	3. Solid content A (Paint)	• 28% +/- 2%
	4. Solid content B (1°hardner)	• /
	5. Solid content A+B (paint+1°hardner)	• /
	6. Pot-life (Life in pot 100 gr/20°C)	• Unlimited
	7. Practical useful life at 20°C 60% U.r.	• Unlimited
	8. Dust free at 20°C, 60% U.r	• 30-40 min
	9. Touch dry at 20°C, 60% U.r	• 2 – 3 h
	10. Dry in deepness at 20°C 60% U.r	• 24 hours
	11. Forced drying 40-45°C	• /
	12. Light stability	• Excellent

Application : Spray, brush, roller.

	Code - Information	Specific weight	mix by gr.	mix by ml.
Paint :	2665**/AZ	1,02	100	100
1°Hardner :	IV220/AZ - Catalyst for outdoor use	1,18	20	17
Thinner :	Water	1,00	10	10

- Quantity to be applied :** • 100 - 120 gr/sqm by hand according to needs.
- Sanding :** • After 24 h at 20°C.
- Over coating :** • Without sanding after 60'-90' with the same product.

Invebi does not assume any responsibility for the improper use of products.

All information and advices (oral, written or any other form) provided by Invebi, even if representing the highest level of our knowledge, can not be considered legally relevant. Our support does not exempt the customer from the duty of previously verifying all information and advices with particular reference to technical and safety data sheets.

IT IS A DUTY OF THE CUSTOMER TO MAKE SURE THAT THE USE OF OUR PRODUCTS IS SUITABLE BEFORE THE APPLICATION AND IN ACCORDANCE WITH ITS REQUIREMENTS, LAWS, REGULATIONS AND PATENTS IN FORCE.



Technical data sheet

INVEBI Industrial coatings – Italy

Storage :

at 20°C **8** months (in the original sealed packing) part A

at 20°C **6** months (in the original sealed packing) part B

please note that the water-based products must always be kept at a temperature higher than 5 ° C to avoid freezing.

General notes :

always mix the products before use

N°3 - 20/10/2017

Invebi does not assume any responsibility for the improper use of products.

All information and advices (oral, written or any other form) provided by Invebi , even if representing the highest level of our knowledge, can not be considered legally relevant. Our support does not exempt the customer from the duty of previously verifying all information and advices with particular reference to technical and safety data sheets.

IT IS A DUTY OF THE CUSTOMER TO MAKE SURE THAT THE USE OF OUR PRODUCTS IS SUITABLE BEFORE THE APPLICATION AND IN ACCORDANCE WITH ITS REQUIREMENTS, LAWS, REGULATIONS AND PATENTS IN FORCE.