


UNIPRIMER

Acrylic-Based Primer

UNIPRIMER is an acrylic-based interior and exterior primer.



Enhances the hiding power and adhesion of the topcoat paint.

Reduces the absorbency of the surface, thereby decreasing paint consumption.

Has high opacity.

Water-based, environmentally friendly, and safe for human health.

 CONTENT: <i>Acrylic-based - water-based</i>	 PACKAGING: <i>2,5 L ; 7,5 L ; 15 L</i>
 THINNING: <i>Diluted with 20-25% clean water</i>	 DRYING TIME: <i>Drying Time Touch dry (at 23°C): 4-5 hours</i> *drying time may be longer at higher relative humidity and lower temperature.
 PRIMER: -	 Fully Dry: <i>24 hours</i>
 APPLICATION TOOL: <i>Roller, brush, spray</i>	 COLORING: -
 NUMBER of COATS: <i>1</i>	 VOC: <i>EU limit value (Directive 2004/42/EC)</i> <i>Category A/G: Primers (water-based): 30 g/L (2010)</i> <i>UNIPRIMER contains a maximum of 29.2 g/L VOC.</i>
 STORAGE and SHELF LIFE: <i>Can be stored unopened for 2 years in a cool and dry place, protected from direct sunlight, between +5°C and +35°C.</i>	

CONSUMPTION - Single Coat : *Consumption may vary depending on the type, absorbency, and structure of the surface, as well as the application techniques. For precise consumption, a controlled sample application should be performed.*



1 L covers 14.5–16.5 m²,
1 kg covers 9.5–11.5 m².
Paint consumption for 1 m²: 60–70 ml and 85–105 g.

APPLICATION AREA

Used as a primer for acrylic-based paints and coating materials on all types of mineral surfaces such as concrete, gas concrete, pressed brick, or fine plaster, for both interior and exterior.

SURFACE PREPARATION

All dirt, oil, blistered paints, and dust must be removed from the surface before application. Surface imperfections should be repaired with San Deco Acrylic Putty Fine for interiors or San Deco Acrylic Putty Coarse for exteriors.

SURFACE CONDITIONS

During application and until the product is fully dry, the ambient and surface temperature should be between +5°C and +35°C.

Ambient humidity should be below 75%.

Surface moisture should be below 10%.

APPLICATION

Before application, Uniprimer should be diluted with 20–25% clean water and mixed until homogeneous.

Apply one coat to the surface using a roller, brush, or spray method.

HAZARD & PRECAUTIONARY STATEMENTS

H317: May cause an allergic skin reaction.
P261: Avoid breathing dust/fume/gas/mist/vapors/spray.
P333+P313: If skin irritation or rash occurs: Get medical advice/attention.
P362+P364: Take off contaminated clothing and wash before reuse.
P280: Wear protective gloves/protective clothing/eye protection/face protection.
P321: Specific treatment (see label).
P272: Contaminated work clothing should not be allowed out of the workplace.

Note: For more information, refer to the product's Safety Data Sheet (SDS).



Complies with TS 13744.

This technical data sheet is prepared based on laboratory results under normal conditions. Please consult technical personnel for additional details. The manufacturer is not responsible for errors resulting from insufficient information. The right to make changes to this information is reserved by our company. Detailed information about product safety, transport, and handling can be found in the Safety Data Sheet.

This product is manufactured by Deka Boya Sanayi ve Tic. A.Ş., which holds certificates of conformity with ISO 9001, ISO 14001, ISO 14064, ISO 45001, and ISO 27001 standards.